

UTILITY PATENT APPLICATION TRANSMITTAL LETTER
(Only for nonprovisional applications under 37 CFR 1.53(b))Assistant Commissioner for Patents
Washington, D.C. 20231
Box PATENT APPLICATION

Transmitted herewith for filing in the patent application of:

Richard G. Henry**ZERO VOLITILE ORGANIC SOLVENT COMPOSITIONS**

Prior U.S. Applications:


This application is a continuation-in-part of U.S. Application Serial No. 09/022,779, filed February 12, 1998, which claims the benefit of the filing date of U.S. Provisional Application Serial No. 60/053,073, filed July 18, 1997.

Enclosed are:

☒ 19 sheets of specification, 6 sheets of claims, 1 sheet of Abstract.
☐ No drawings with Application.
☒ an assignment of an invention to (and transmittal therefor).
☒ a Declaration and Power of Attorney for Patent Application.
☒ Information Disclosure Statement and PTO-1449.
☒ Petition to Make Special Under 37 C.F.R. § 1.102(c).

CLAIMS AS FILED				
FOR	NO. FILED	NO. EXTRA	RATE	FEE
TOTAL CLAIMS	22 - 20 =	2	[] \$18 LARGE [XX] \$09 SMALL	\$ 18.00
INDEPENDENT CLAIMS	10 - 3 =	7	[] \$78 LARGE [XX] \$39 SMALL	\$273.00
BASIC FEE	[] LARGE ENTITY \$690	[XX] SMALL ENTITY \$345		
TOTAL FILING FEE				\$636.00

☒ A check in the amount of \$636.00 to cover the filing fee is enclosed.☒ The Commissioner is hereby authorized to charge any additional fees which may be required at any time during the prosecution of this application without specific authorization, or credit any overpayment to Deposit Account No. 06-0308.2/29/00
Date


 Attorney of Record
 Timothy E. Nauman, Reg. No. 32,283
 Brian G. Bembenick, Reg. No. 41,463
 FAY, SHARPE, FAGAN,
 MINNICH & McKEE, LLP
 1100 Superior Avenue, Seventh Floor
 Cleveland, Ohio 44114-2518
 (216) 861-5582

EXPRESS MAIL CERTIFICATEI hereby certify that this Utility Patent Application Transmittal Letter and accompanying papers are being deposited with the United States Postal Service "Express Mail Post Office To Addressee" service under 37 C.F.R. 1.10 and is addressed to the Assistant Commissioner For Patents, Box Patent Application, Washington, D.C. 20231 on _____ EXPRESS MAIL NO.: EL530713922US

Name

Charles Dunsbar

PATENT**IN THE UNITED STATES PATENT AND TRADEMARK OFFICE**

IN RE APPLICATION OF : Richard G. Henry
FOR : ZERO VOLATILE ORGANIC
SOLVENT COMPOSITIONS
SERIAL NO. : Unknown
FILED : Herewith
EXAMINER : Unknown
ART UNIT : Unknown
ATTORNEY DOCKET NO. : ACD 2 0016-1-3

Cleveland, Ohio 44114-2518

STATEMENT CLAIMING SMALL ENTITY STATUS
(37 CFR 1.9(f) & 1.27(d))—SMALL BUSINESS CONCERN

Assistant Commissioner of Patents
Washington, D.C. 20231

Dear Sir:

I hereby state that I am

☐ the owner of the small business concern identified below:
☒ an official of the small business concern empowered to act on behalf
of the concern identified below:

NAME OF SMALL BUSINESS CONCERN: Polymer Solvents LLC

ADDRESS OF SMALL BUSINESS CONCERN: 17 Bordeaux Lane
Beachwood, OH 44122

I hereby state that the above identified small business concern qualifies as a small business concern as defined in 13 CFR Part 121 for purposes of paying reduced fees to the United States Patent and Trademark Office. Questions related to size standards for a small business concern may be directed to: Small Business Administration, Size Standards Staff, 409 Third Street, SW, Washington, DC 20416.

I hereby state that rights under contract or law have been conveyed to and remain with the small business concern identified above with regard to the invention described in:

- ☒ the specification filed herewith with title as listed above.
- ☐ the application identified above.
- ☐ the patent identified above.

If the rights held by the above identified small business concern are not exclusive, each individual, concern, or organization having rights in the invention must file separate statements as to their status as small entities, and no rights to the invention are held by any person, other than the inventor, who would not qualify as an independent inventor under 37 CFR 1.9(c) if that person made the invention, or by any concern which would not qualify as a small business concern under 37 CFR 1.9(d), or a nonprofit organization under 37 CFR 1.9(e).

Each person, concern, or organization having any rights in the invention is listed below:

- ☒ no such person, concern, or organization exists.
- ☐ each such person , concern, or organization, if any, is listed below:

Separate statements are required from each named person, concern or organization having rights to the invention stating their status as small entities. (37 CFR 1.27)

I acknowledge the duty to file, in this application or patent, notification of any change in status resulting in loss of entitlement to small entity status prior to paying, or at the time of paying, the earliest of the issue fee or any maintenance fee due after the date on which status as a small entity is no longer appropriate. (37 CFR 1.28(b))

NAME OF PERSON SIGNING: Richard G. Henry

TITLE OF PERSON:

President

ADDRESS OF PERSON SIGNING:

17 Bordeaux Lane
Beachwood, OH 44122

SIGNATURE:

Richard G. Henry

DATE:

02/25/00

ZERO VOLITILE ORGANIC SOLVENT COMPOSITIONS

This application is a continuation-in-part of U.S. Application Serial No. 09/022,779, filed February 12, 1998, which claims the benefit of the filing date of U.S. Provisional Application Serial No. 60/053,073, filed July 18, 1997.

5

Background of the Invention

This invention pertains to the art of solvent blends and solvent/resin blends. More particularly, this invention pertains to blends that reduce the atmospheric reactivity of some high volatile organic compounds. The invention is particularly applicable to solvent blends and solvent/resin blends that combine volatile organic
10 compounds with newly discovered zero volatile organic compounds for use adhesives, coatings, inks, cleaning and blowing agents and the like and will be described with particular reference thereto. However, it will be appreciated that the invention may be advantageously employed in other environments and applications.

15 Heretofore, hydrocarbon-based solvents have been used to dissolve organic materials in many industrial applications. However, recently, hydrocarbon-based solvents have fallen out of favor because they have been classified by the United States Environmental Protection Agency and other international regulatory bodies as materials that contribute to the formation of ground based ozone or
20 smog. This has created a need for other types of solvents for the production of coatings, adhesives, inks and the like.

Upon evaporation, a highly-reactive, hydrocarbon-based solvent reacts with hydroxyl radicals and ultraviolet light very close to the ground to form a photochemical smog that is considered harmful and in some cases dangerous.
25 Some cities have severe smog which reduces visibility and actually causes "ozone alerts." In part, the smog is caused by hydrocarbon emissions from cars. However, another major contributor is industrial use of hydrocarbon-based solvents such as hexane and toluene.

For the purpose of ozone exceedence in cities throughout the United States,
30 a reactivity based formulation scheme will also be described which will make use of low atmospheric reactivity solvents by themselves or in combination with high

reactivity solvents. These solvents and solvent blends can be used to dissolve resins for adhesives, inks and coatings, or used as cleaning agents and in the process reduce the amount of ozone formed in the lower atmosphere.

The benchmark for desired reaction rates of hydrocarbon-based compounds is ethane. If a compound has a reaction rate with the hydroxyl radical and ultraviolet ("UV") light that is faster than ethane, the compound reacts too close to the ground and consequently generates ozone and smog. Such compounds are defined as volatile organic compounds (VOCs). On the other hand, if a compound has a reaction rate that is slower than ethane, the compound reaches higher into the atmosphere before reacting with the hydroxyl radical and UV light. In such instances the non-VOC compound does not contribute to the formation of ground based ozone and smog.

Governmental regulations limit the use of VOCs in coatings, inks, and adhesives. As a result, water-borne coatings have become the most important type of coatings in coating and adhesive systems. However, water-borne coatings must contain some volatile organic compound content. This is because water flashes off too fast from the water-based latex or emulsion to make a good film. To alleviate this problem, 7% to 10% of a slower evaporating solvent such as a glycol ether is added to the latex to aid in film formation. Unfortunately, glycol ethers are primary examples of VOCs and thus dangerous to the environment.

Halogenated hydrocarbon-based compounds have reaction rates that are slower than ethane. However, these halogenated compounds are ozone depleting consequently, they are not suitable VOC-free solvents.

In the prior art, United States Patent No. 5,102,563 to Desbiendras describes a solvent composition which contains methyl tert butyl ether. However, methyl tert butyl ether is a VOC and thus unsafe for the environment. Similarly, Patent No. 4,898,893 to Ashida describes a composition for making a blowing agent which contains a flammable aliphatic hydrocarbon. This is also a VOC. Patent No. 3,950,185 to Toyama teaches film removing compositions which contain methylene chloride and bromochloromethane which are not VOCs. However, these compositions also contain methanol and monochlorobenzene which are VOCs. Patent No. 3,924, 455 to Begishagen describes a formulation containing mineral

spirits which removes lacquer stress coatings. These mineral spirits are also VOCs.

Use of a combination of a zero volatile compound with a highly reactive compound or with a low reactivity compound will reduce the overall VOC content of the mixture when used for the applications mentioned. Also, various low reactivity VOC solvents have been identified which when used with resins, will reduce the atmospheric reactivity of the coating, ink or adhesive. The low reactivity solvents can be blended with high reactivity solvents before mixing with a resin to lower the total reactivity of the formulation. Thus, the highly reactive compounds become less reactive than just a subtractive effect in some instances. In other examples, it takes a larger amount of the zero volatile organic compound to give the desired effect of reducing the incremental reactivity of the mixture closer to 0.25, which is the value measured for ethane.

Some highly reactive VOC solvents do not realize the same degree of VOC activity reduction according to the present application as other VOCs. Examples of these are formaldehyde, methyl nitrite, trans-2-butene, and 1,3,5-trimethylbenzene. These compounds are so reactive that addition of a zero VOC compound will have little or no effect on the reactivity of the mixture. A first object of the present invention is to provide a reduction in atmospheric activity of high VOC solvents by adding a zero VOC solvent to the high VOC solvent. An additional aspect to the present invention involves producing environmentally friendly coatings, inks, adhesives, blowing agents and cleaning agents by adding a zero VOC solvent to a high VOC solvent containing coating, ink, adhesive, blowing agent or cleaning agent.

A first object of the invention is to provide a reduction in atmospheric reactivity of high VOC solvents by addition of a low reactivity or zero VOC solvent to the high VOC solvent.

An additional aspect of the present invention involves producing environmentally friendly coatings, inks, adhesives, blowing agents and cleaning agents by adding a zero VOC or low reactivity solvent to a high VOC solvent containing coating, ink, adhesive, blowing agent or cleaning agent.

A further object of the present invention is the identification of some high-performance solvents and solvent/resin blends which are non-flammable or self-extinguishing and do not contribute to the formation of ground-based ozone.

Another object of the present invention are solvents and solvent/resin blends that are safer to the environment than even water-based systems which still must contain a volatile organic solvent to aid in film formation.

Yet another object of the present invention are environmentally-safer solvent compositions which do not contribute to the formation of ground based ozone which will be useful in the formulation of cleaning agents, coatings, adhesives, inks and also blowing agents for the production of plastic foams.

Summary of the Invention

The present invention is directed to reduced incremental atmospheric reactivity of volatile organic compound based compositions using zero volatile organic chemical compounds (VOC) and VOC compounds with low atmospheric reactivity which overcome all of the above referenced problems and others and which are economical and effective for their intended uses.

In accordance with a first aspect of the present invention, there is provided a solvent system wherein a high VOC solvent has its atmospheric activity reduced by addition thereto of a low reactivity or zero VOC solvent.

In accordance with a further aspect of the invention, coatings, inks, adhesives, blowing agents and cleaning agents containing VOC solvents are made environmentally friendly through reduction of atmospheric reactivity by addition of a zero VOC or low reactivity VOC solvent to the VOC composition.

In a further aspect of the invention, VOC solvents have their atmospheric reactivity reduced to approach 0.25 (the measured value for ethane) by addition thereto of a low reactivity or zero VOC solvent thereby rendering the VOC solvent composition environmentally friendly.

In accordance with a second aspect of present invention, there is provided a solvent-resin composition having a combination of a zero volatile compound with a highly reactive compound or with a low reactivity compound. The solvent component is about 5% to about 95% by total volume of the solvent-resin

composition and is one or more of the zero VOC solvents selected from the group consisting of:

- 5 1-bromopropane;
 benzotrifluoride;
 t-butylacetate;
 methyl acetate;
 parachlorobenzotrifluoride;
 acetone;
10 1,1,1,2,2,3,3,4,4-nonafluoro-4-methoxybutane;
 1-ethoxy-1,1,2,2,3,3,4,4, 4-nonafluorobutane;
 2-(ethoxydifluoromethyl)-1,1,1,2,3,3,3- heptafluoropropane;
 technical white oils; and,
 n-alkane (C12-C18).

15 In accordance with a more limited aspect of the invention, from about 0.1% by volume to about 98% by volume of the VOC solvents can be blended with the zero VOC solvents to act as a solvent carrier for any of the mentioned resin systems.

20 A principal advantage of the invention is that the VOC solvents are rendered environmentally safer yet still capable of effectively dissolving resins.

 Another advantage of the invention is that it may be used in place of solvents currently used for inks, adhesives, coatings and the like.

25 Still other advantages and benefits of the invention will become apparent to those skilled in the art upon a reading and understanding of the following detailed description.

Detailed Description of the Preferred Embodiments

30 The compositions of the present invention are high-performance solvent and solvent-resin blends that have reduced atmospheric reactivity. In addition, compositions which are generally VOC-type are also disclosed. The compositions as herein described and as set forth in the claims are expressed in terms of percentages of volume unless clearly indicated to the contrary.

In describing the compositions of the present invention, reference will be made to certain resin classifications which require a totally VOC-free solvent system to be environmentally safe. These resin classifications are:

- 5 a) acrylic-thermoplastic;
- b) acrylic-thermosetting;
- c) chlorinated rubber;
- d) epoxy (either one or two part);
- e) hydrocarbon (e.g., olefins, terpene resins, rosin esters, coumaroneindene, styrene-butadiene, styrene, methyl-
- 10 styrene, vinyl-toluene, nitrocellulose, polychloroprene, polyamide, polyvinyl chloride and isobutylene);
- f) phenolic;
- g) polyester and alkyl;
- h) polyurethane;
- 15 i) silicone;
- j) urea; and,
- k) vinyl and vinyl acetate.

It is to be appreciated that this list does not include all resin classifications. Other resin classifications are intended to be encompassed by the scope of the present
20 invention.

Examples of VOC solvents that have their maximum incremental reactivity effected are:

- xylene;
- toluene;
- 25 glycol ethers;
- trichloroethylene;
- naphthenic solvents;
- iso-paraffins;
- epoxides;
- 30 acetals;
- nitroparaffins;
- n-methyl pyrrolidone;
- hexane;

5 terpene;
 dimethyl ether;
 esters;
 ketones;
 ethyl acetate;
 alcohols;
 paraffins;
 oxygenated solvents;
 propylene carbonate;
 10 mineral spirits; and,
 dibasic esters.

Effective solvents of the present invention which have reaction rates with hydroxyl ion slower than ethane (i.e., < 0.25) are:

- 15 1) 1-bromopropane;
- 2) benzotrifluoride;
- 3) t-butylacetate;
- 4) methyl acetate;
- 5) parachlorobenzotrifluoride;
- 6) acetone;
- 20 7) 1,1,1,2,2,3,3,4,4-nonafluoro-4-methoxybutane;
- 8) 1-ethoxy-1,1,2,2,3,3,4,4, 4-nonafluorobutane;
- 9) 2-(ethoxydifluoromethyl)-1,1,1,2,3,3,3-
 eptafluoropropane;
- 10) technical white oils;
- 25 11) n-alkane (C12-C18);
- 12) chlorobromomethane;
- 13) perchloroethylene;
- 14) 1,2 dichloro-1,1,2-trifluoroethane;
- 15) dimethoxymethane;
- 30 16) 2-(difluoromethoxymethyl)-1,1,1,2,3,3,3-
 heptafluoropropane; and
- 17) methylene chloride;

It is to be appreciated that this list does not include all effective non-VOC solvents. Other effective non-VOC solvents are intended to be encompassed by the scope of the present invention.

5 Atmospheric reactivity of VOC solvent compositions can be reduced by from about 20% to about 90% upon addition of an effective amount of a zero VOC solvent or a low reactivity VOC solvent. The amount of zero VOC or low reactivity VOC solvent which is effective for reducing the atmospheric reactivity of VOC solvent compositions can range in amounts of from about 0.1% by volume to about 99.9% by volume of the solvent composition.

10 The type of specific applications (hence the denotation "a" alongside the number identifying the application) for which the solvents and solvent-resin blends of the present invention may be used are as follows:

- 1a) adhesives
- 2a) blowing agents
- 15 3a) coatings
- 4a) cleaning compositions
- 5a) inks

The zero VOC solvent and solvent-resin blends of the present invention as well as their applications are set forth in the table below. The table uses the
20 identifiers set out above, i.e., a numeral alone for the solvent and a number followed by a "a" for the application.

	VOC Compounds (more reactive than ethane)	Maximum Incremental Reactivity (MIR)*	% by volume of Zero VOC compound necessary to reduce reactivity by 20% to 90%	Applications
5	A. xylene	6.5-8.2	5-98	1a-5a
	B. n-methyl pyrrolidone	1.25	5-98	1a-5a
	C. Toluene	2.70	5-98	1a-5a
	D. terpenes	3-4.4	5-98	1a-5a
	E. Glycol ethers	0.44	10-99.9	1a-5a
10	F. Oxygenated solvents	0.40-1.40	10-99.9	1a-5a
	G. TCE	0.75	5-98	1a-5a
	H. dimethyl ether	0.76	10-80	1a-5a
	I. Napthenic solvents	2.7	5-98	1a-5a
	J. Dibasic esters	0.75-1.5	5-90	1a-5a
15	K. Paraffins	0.32-1.6	5-95	1a-5a
	L. Hexane	0.98	5-95	1a-5a
	M. Isoparaffins	0.37-1.4	5-95	1a-5a
	N. Ketones	0.56-1.18	5-95	1a-5a
	O. Epoxides	0.60-1.30	10-99.9	1a-5a
20	P. ethyl acetate	0.55-1.23	5-98	1a-5a
	Q. Acetals	0.33	30-99.9	1a-5a
	R. Nitroparaffins	0.80	30-99.9	1a-5a
	S. Alcohols	0.42-2.7	10-99.9	1a-5a
25	t-butyl alcohol	1.0	10-99.9	1a-5a
	isopropanol	0.54	10-98	1a-5a
	n-propyl alcohol	2.3	10-98	1a-5a
	methanol	0.56	10-98	1a-5a
	propylene carbonate	0.75	10-98	1a-5a
30	mineral spirits	0.83-89	10-98	1a-5a
	* ethane	0.25		

A better understanding of the present invention can be had by reference to the following descriptions of embodiments which effectively meet the objectives outlined above.

One preferred embodiment of a reduced reactivity solvent blend is to select a high reactivity solvent (MIR greater than 1), such as toluene, and blend it with a low reactivity solvent (MIR less than 1) such as isopropyl alcohol to reduce the total reactivity of the solvent blend. Though neither compound is VOC exempt, the combination of the two will be safer to the environment. This mixture will be useful in combination with a resin to produce an adhesive, coating or ink. Any high reactivity solvent can be used in place of the toluene.

An embodiment of a reduced reactivity solvent blend is to select a high reactivity solvent (MIR greater than 1) such as toluene, xylene, glycol ethers, hexane or mineral spirits and blend it with a zero VOC solvent such as 1-bromopropane, benzotrifluoride, t-butylacetate, methyl acetate, or acetone to reduce the total reactivity of the solvent blend. This mixture will be useful in combination with a resin to produce an environmentally friendly adhesive, coating, ink or blowing agent having a reduced atmospheric reactivity.

The following examples are intended to be exemplary of the present invention and are not intended to limit the invention of the particular embodiments described therein.

Examples

5 The following solvent systems are in accordance with the present invention:

Example No.	VOC Solvent: Xylene*	Zero VOC Solvent: 1-bromo propane*
1	30	70
2	20	80
10 3	10	90

* amounts based on percent volume in a 100g blend.

15 The solvent blends set forth above are added to 5 to 30 grams hydrocarbon resin such as an olefin, terpene, methacrylate or other tackifier followed by addition of 10 to 35 grams of a polymeric resin such as a styrene-butadiene, acrylic, epoxy, polychloroprene, urethane, natural rubber or styrene. This mixture produces a contact adhesive with excellent bond strength. Any of the above listed VOC solvents mentioned above can be used in place of the xylene.

20 Another preferred embodiment contains 0.1% to 30% by volume of an epoxide, acetal, nitroparaffin, glycol ether, alcohol or combination thereof and 70% to 99.9% of 1-bromopropane to form a reduced VOC solvent mixture. This mixture is then added to 5% to 35% by weight of a hydrocarbon resin, and 5% to 35% of a styrene-butadiene polymer, a polychloroprene polymer, polyvinyl chloride
25 polymer, natural rubber polymer, acrylic, epoxy, urethane, nitrocellulose or styrene polymer.

 Another preferred embodiment of a reduced VOC solvent composition is 100 grams of a mixture containing 5% to 99.9% by volume of either benzotrifluoride, t-butylacetate, methyl acetate or parachlorobenzotrifluoride or a
30 combination thereof and a portion of high VOC solvent mentioned above so that the incremental reactivity of the mixture is reduced closer to the incremental reactivity of ethane (0.25) this mixture can be combined with a resin to produce a coating, ink, adhesive or used as is for a cleaning agent.

An embodiment of a polyurethane foam process using an environmentally safer blowing agent according to the invention is as follows:

- 1 to 100 parts by weight of a polyol
- 1 to 50 parts by weight of toluene diisocyanate or methylene diphenylene diisocyanate
- 2 parts by weight water
- 0.15 to 0.80 parts catalyst
- 0.5 to 2 parts surfactant; and
- 4 to 20 parts acetone or methyl acetate

All of the embodiments of the present invention may interchangeably use any of the other non-VOC solvents listed above.

The following embodiments represent zero VOC solvent compositions wherein the solvent consists essentially of the zero VOC solvent.

Solvent and Solvent-resin Compositions Having Zero VOC's

	Main Component	How Used (blends are 5% to 95% or, more preferably, 40% to 95% by vol.)	Resins That Form a Film after Solvent Evaporates	Applications
	chlorobromomethane	by itself or blended with any of solvents 2-16 to obtain desired properties	a-k	1a-5a
	1-bromopropane	by itself or blended with solvents 1, 3-16	a-k	1a, 3a, 5a
	methyl acetate	blended with solvents 1,2, 4-16 at 10-95% by volume.	a-d, styrene, g, j, k	1a-5a
	n-alkane (C12-C18)	by itself or blended with solvents 1-3,5-16	e	1a, 3a, 4a, 5a
	t-butylacetate	by itself or blended with solvents 1,4,6-16	a-d, styrene, g, j, k	1a, 3a, 4a, 5a
	perchloroethylene	1-5,7-16	a-k	1a,3a,4a,5a
	benzotrifluoride	1-6, 8-16	a-k	1a,3a,4a,5a
	parachlorobenzotrifluoride	1-7, 9-16	a-k	1a,3a,4a,5a
	acetone	1-5,7-16	a, b, e-h, k	1a-5a
	1,2-dichloro-1,1,2- trifluoroethane	1-9, 11-16	a, k	1a-5a

	Main Component	How Used (blends are 5% to 95% or, more preferably, 40% to 95% by vol.)	Resins That Form a Film after Solvent Evaporates	Applications
20	dimethoxymethane	1-3,7-10, 12-16	a	1a-5a
	1,1,1,2,2,3,3,4,4- nonafluoro-4-methoxy- butane	1-11, 13,15	a	2a, 4a
5	2-(difluoromethoxymethyl)- 1,1,1,2,3,3,3- heptafluoropropane	1-12, 14,15	a	2a, 4a
	1-ethoxy-1,1,2,2,3,3,4,4,4- nonafluorobutane	1-13, 15	a	2a,4a
10	2-(ethoxydifluoromethyl)- 1,1,1,2,3,3,3- heptafluoropropane	1-4	a	2a,4a
	methylene chloride	2-15	a-k	1a-5a
15	technical white oils (mineral)	1-16	a,e,g	5a

A better understanding of the present invention can be had by reference to the following descriptions of embodiments which effectively meet the objectives outlined above.

20 One preferred embodiment includes mixing one or more of the polymeric resins:

25 acrylic-thermoplastic;
acrylic-thermosetting;
chlorinated rubber;
epoxy resin;
hydrocarbon (e.g., olefins, terpene resins, rosin esters, coumarone-indene, styrene-butadiene, styrene, methylstyrene, vinyl-toluene, nitrocellulose, polychloroprene, polyamide, polyvinyl chloride and isobutylene);
30 phenolic;
polyester and/or alkyd;
polyurethane;
silicone;
urea; and/or

vinyl or vinyl acetate,
with 10-90%, by total volume of the composition, of one or more of non-VOC
solvents such as:

- 5 chlorobromomethane;
- 1-bromopropane;
- methyle acetate;
- n-alkane (C12-C18);
- t-butylacetate;
- perchloroethylene;
- 10 benzotrifluoride;
- parachlorobenzotrifluoride;
- acetone;
- 1,2-dichloro-1,1,2-trifluoroethane;
- dimethoxymethane; and/or
- 15 methylene chloride.

The individual solvents or blends thereof are added until all of the resin(s) is
dissolved.

In an embodiment for coatings and/or adhesives, the mixture preferably has
a high resin content, i.e., a resin content of 20% to 60% by volume. In another
20 embodiment for inks, the mixture preferably contains a lower concentration of the
resin, i.e., 5% to 30% by volume. In yet another embodiment, various pigments or
additives are added to achieve a desired range of properties.

In another preferred embodiment of the present invention, 5% to 90%
methyle acetate, by total volume of the composition, is added to 10% to 95% of a
25 solvent or solvent blend selected from the group:

- chlorobromomethane;
- 1-bromopropane;
- n-alkane (C12-C18);
- t-butylacetate;
- 30 perchloroethylene;
- benzotrifluoride;
- parachlorobenzotrifluoride;
- acetone;

1,2-dichloro-1,1,2-trifluoroethane;
dimethoxymethane;
1,1,1,2,2,3,3,4,4-nonafluoro-4-methoxy-butane;
2-(difluoromethoxymethyl)-1,1,1,2,3,3,3-heptafluoropropane;
5 1-ethoxy-1,1,2,2,3,3,4,4,4-nonafluorobutane; and,
2-(ethoxydifluoromethyl)-1,1,1,2,3,3,3-heptafluoropropane.

These formulations are used as a cleaning composition for the removal of hydrocarbon or ionic contaminants from circuit boards or in the formulation of coatings, inks, or adhesives. Of course, the formulations may be used for other
10 applications as well.

The following enumerated embodiments have the ability to dissolve resins for the production of coatings, adhesives, and inks as well. In addition, the embodiments are equally useful as cleaning formulations. The ranges for the
15 embodiments are expressed in % by volume of the total solvent-resin composition or, alternatively, the total solvent composition of an initially non-resin containing solvent, such as a cleaning composition. The embodiments are:

- (1) 10% to 90% benzotrifluoride and 10-90% of one or more of the solvents:
 - (a) 1,1,1,2,2,3,3,4,4-nonafluoro-4-methoxy-butane;
 - 20 (b) 2-(difluoromethoxymethyl)-1,1,1,2,3,3,3-heptafluoropropane;
 - (c) 1-ethoxy-1,1,2,2,3,3,4,4,4-nonafluorobutane;
 - (d) 2-(ethoxydifluoromethyl)-1,1,1,2,3,3,3-heptafluoropropane;
 - 25 (e) perchloroethylene;
 - (f) 1-bromopropane;
 - (g) acetone;
 - (h) n-alkane (C12-C16);
 - (i) t-butyl acetate (C12-C16); and,
 - 30 (j) parachlorobenzotrifluoride;
- (2) 5% to 20% benzotrifluoride and 80% to 95% 1-bromopropane;
- (3) 10% to 90% acetone and 10-90% n-alkane(C12-C18);

- 5 (4) 10% to 90% 1-bromopropane and 10% to 90% of one or more of:
- (a) chlorobromomethane; and,
 - (b) n-alkane (C12-C18);
- 10 (5) 10% to 90% parachlorobenzotrifluoride and 10% to 90% of one or more of:
- (a) 1-bromopropane;
 - (b) chlorobromomethane;
 - (c) t-butylacetate; and,
 - (d) n-alkane (C12-C18);
- 15 (6) 10% to 90% 1,2-dichloro-1,1,1-trifluoroethane and 10% to 90% of one or more of:
- 1,1,1,2,2,3,3,4,4-nonafluoro-4-methoxy-butane;
 - 2-(difluoromethoxymethyl)-1,1,1,2,3,3,3-heptafluoropropane;
 - 1-ethoxy-1,1,2,2,3,3,4,4,4-nonafluorobutane;
 - and,
 - 2-(ethoxydifluoromethyl)-1,1,1,2,3,3,3-heptafluoropropane;
- 20 1-bromopropane
- acetone;
- benzotrifluoride; and,
- methyl acetate.

25 Analogously, the following VOC-free embodiment has the ability to dissolve resins for the production of coatings, adhesives, and inks as well. In addition, the embodiment is equally useful in cleaning formulations:

- 30 (1) 10% to 90% methylene chloride and 10% to 90% of one or more of the following solvents:
- chlorobromomethane;
 - 1-bromopropane;
 - methyl acetate;
 - n-alkane (C12-C18);
 - t-butylacetate;

- perchloroethylene;
benzotrifluoride;
parachlorobenzotrifluoride;
acetone;
5 1,2-dichloro-1,1,2-trifluoroethane; and,
dimethoxymethane.

An added benefit to mixing methylene chloride with other solvents is the reduction in the overall toxicity of methylene chloride.

Other preferred solvent-resin compositions include VOC-free solvents
10 which have the ability to dissolve resins for the production of coatings, adhesives, and inks. The compositions include any of the above-listed resins and the following solvent mixtures, which are expressed in terms of % by volume of the solvent-resin composition:

- 15 (1) 1% to 20% technical white oil and 10% to 90% n-alkane (C12-C18);
(2) 1% to 20% technical white oil and 10% to 90% methyl acetate;
(3) 1% to 20% technical white oil and 10% to 90% t-butylacetate;
20 (4) 1% to 20% technical white oil and 10% to 90% benzotrifluoride;
(5) 1% to 20% technical white oil and 10% to 90% acetone;
(6) 1% to 20% technical white oil and 10% to 90% parachlorobenzotrifluoride;
25 (7) 1% to 20% technical white oil and 10% to 90% parachlorobenzotrifluoride;
(8) 1% to 20% technical white oil and 10% to 90% perchloroethylene;
30 (9) 1% to 20% technical white oil and 10% to 90% methylene chloride; and,

- (10) 1% to 20% technical white oil and 10% to 90% of a mixture of methylene chloride, acetone, t-butylacetate, methyl acetate and perchloroethylene.

5 The following VOC-free embodiment, expressed in terms of % by volume of total composition, is useful as an environmentally-safer blowing agent composition for the production of polyurethane or isocyanurate foams:

99% to 99.98% 1,2-dichloro-1,1,1-trifluoroethane and
0.01% to 0.5% alpha-methyl styrene to inhibit polymerization.

10 In addition this embodiment has the ability to dissolve resins for the production of coatings, adhesives, and inks, and is useful in cleaning formulations.

Another embodiment which is useful in an environmentally-safer urethane blowing production process comprises using a zero VOC blowing agent composition comprising:

15 100 parts by weight polyether triol;
50 parts by weight toluene diisocyanate or toluene disocyanurate;
2 parts by weight water;
0.15 parts catalyst;
0.5 to 2 parts surfactant; and,
20 4 to 10 parts 1-bromopropane or chlorobromomethane.

Still another embodiment which is useful in a urethane production process comprises an environmentally-safer blowing agent composition, wherein the composition comprises, in terms of percent by weight of the total composition (including catalyst and surfactant):

25 50% to 70% polyether triol;
20% to 40% toluene diisocyanate or toluene disocyanurate;
0% to 10% water;
0% to 5% catalyst;
0% to 5% surfactant;
30 2% to 15% 1-bromopropane or chlorobromomethane.

The appropriate catalysts and surfactants are selected from those known in the art.

A more limited embodiment which is useful in a urethane production process comprises an environmentally-safer blowing agent composition, wherein

the composition comprises, in terms of percent by weight of the total composition (including catalyst and surfactant):

- 5 60% to 65% polyether triol;
- 30% to 33% toluene diisocyanate or toluene diisocyanurate;
- 1% to 2% water;
- 0.09% to 2% catalyst;
- 0.3% to 1.5% surfactant; and,
- 2.4% to 6.1% 1-bromopropane or chlorobromomethane.

10 This composition is useful for the manufacture of, for example, a flexible furniture grade foam with a density of 0.024 g/cm³.

 An embodiment of a zero VOC adhesive is 350 grams of 1-bromopropane and/or benzotrifluoride to which is added 30% to 50% by weight of a hydrocarbon resin, preferably an olefin, rosin ester or terpene resin, which acts as a tackifier. Then, 100 grams of styrene-butadiene polymer, polychloroprene polymer, polyvinyl
15 chloride polymer, acrylic, epoxy, urethane, nitrocellulose, or styrene is added to the mixture. This mixture produces a contact adhesive with excellent bond strength. Another preferred embodiment of this mixture contains approximately 40% to 90%, volume, of 1-bromopropane and/or benzotrifluoride, 5% to 35% of a hydrocarbon resin, and 5% to 25% of styrene-butadiene polymer, polychloroprene polymer,
20 polyvinyl chloride polymer, acrylic, epoxy, urethane, nitrocellulose, or styrene.

 Another zero VOC adhesive starts with 100 grams of 1-bromopropane and/or benzotrifluoride. Then, 10 to 100 grams of styrene-butadiene, polychloroprene, polyvinyl chloride, acrylic, epoxy, urethane, nitrocellulose, or styrene polymer or resin is added. This also produces a contact adhesive with
25 excellent bond strength. It is appreciated that other additives may be used to improve wetting and defoaming although they are not always required. Another preferred embodiment of this mixture contains approximately 40% to 95%, by volume, of 1-bromopropane and/or benzotrifluoride, and 5% to 60% of styrene-butadiene, polychloroprene, polyvinyl chloride, acrylic, epoxy, urethane,
30 nitrocellulose, or styrene polymer or resin. Still another preferred embodiment of this mixture contains approximately 70% to 95%, by volume, of 1-bromopropane and/or benzotrifluoride, and 5% to 30% of styrene-butadiene, polychloroprene,

polyvinyl chloride, acrylic, epoxy, urethane, nitrocellulose, or styrene polymer or resin.

Still another embodiment of a zero VOC adhesive starts with 350g 1-bromopropane and/or benzotrifluoride. Then, 20 to 100 grams of styrene
5 butadiene rubber is added. Optionally, 5% to 10%, by volume, acetone is added to improve solubility if necessary. Another preferred embodiment of this mixture contains approximately 50% to 90%, by volume, of 1-bromopropane, and 10% to 30% of acrylic polymer or urethane polymer. Optionally, 5% to 10%, by volume, acetone is added to improve solubility if necessary.

10 The following VOC-free embodiment has the ability to dissolve resins for the production of coatings, adhesives, and inks as well. Further, the solvent includes stabilizers to stabilize against attack on aluminum. In addition, the embodiment is useful in cleaning formulations:

70% to 90%, by volume, 1,2-dichloro-1,1,1-trifluoroethane;
15 9% to 29% dimethoxymethane; and
0.5% butylene oxide and 0.5% nitromethane

to stabilize against attack on aluminum. Optionally, 5% to 10%, by volume, acetone is added to the total composition to improve solubility if necessary.

All of the embodiments of the present invention may interchangeably use
20 any of the other non-VOC solvents listed above.

The invention has been described with reference to the preferred
embodiments. Obviously, modifications and alterations will occur to others upon
a reading and understanding of this specification. It is intended to include all such
modifications and alterations insofar as they come within the scope of the
25 appended claims or the equivalents thereof.

The invention has been described with reference to the preferred
embodiments. Obviously, modifications and alterations will occur to others upon
a reading and understanding of this specification. It is intended to include all such
modifications and alterations insofar as they come within the scope of the
30 appended claims or the equivalence thereof.

Having thus described the invention, it is claimed:

1. A solvent-resin composition having reduced atmospheric reactivity, the composition consisting essentially of a resin component and a solvent component, the solvent component being 5% to 95% by total volume of the solvent-resin composition, the solvent component comprising a blend of from about 0.1% to about 99.9% by volume of a zero volatile organic compound (VOC) solvent selected from the group consisting of:

- 1) 1-bromopropane;
- 2) benzotrifluoride;
- 3) t-butylacetate;
- 4) methyl acetate;
- 5) parachlorobenzotrifluoride
- 6) acetone;
- 7) 1,1,1,2,2,3,3,4,4-nonafluoro-4-methoxybutane;
- 8) 1-ethoxy-1,1,2,2,3,3,4,4,4-nonafluorobutane;
- 9) 2-(ethoxydifluoromethyl)-1,1,1,2,3,3,3-heptafluoropropane;
- 10) technical white oils (mineral oils); and
- 11) n-alkane (C12-C18),

blended with from about 0.1% to about 99.9% by volume of a reactive VOC solvent selected from the group consisting of:

- xylene;
- toluene;
- n-methyl pyrrolidone;
- hexane;
- oxygenated solvents;
- propylene carbonate;
- glycol ethers;
- trichloroethylene;
- naphthenic solvents;
- iso-paraffins;
- epoxides;
- acetals;

nitroparaffins;
terpene;
dimethyl ether;
esters;
ketones;
ethyl acetate;
alcohols;
paraffins;
mineral spirits;
dibasic esters;
cycloalkanes; and
cycloalkene.

2. The composition according to claim 1 wherein the solvent component is present in the amount of from about 10% to about 95% by total volume of the composition.

3. The composition according to claim 2 wherein the solvent component is present in the amount of from about 30% to about 80% by total volume of the composition.

4. An adhesive resin-solvent composition comprising:
40% to 90%, by total volume of the composition, of a solvent composition comprising one or more zero VOC solvents selected from 1-bromopropane , benzotrifluoride and t-butylacetate, and a volatile organic compound (VOC) solvent,
5% to 35% of a tackifier, and
5% to 40% of a resin, said resin comprising at least one resin selected from the group consisting of styrene-butadiene, polychloroprene, polyvinyl chloride, acrylic, epoxy, urethane, nitrocellulose, and styrene.

5. The adhesive resin-solvent composition of claim 4, wherein, the zero VOC solvent is benzotrifluoride.

6. The adhesive resin-solvent composition of claim 4 wherein the zero VOC solvent is 1-bromopropane.

7. The adhesive resin-solvent composition of claim 4 wherein the zero VOC solvent is t-butylacetate.

8. A coating or ink resin-solvent composition comprising:
10% to 90%, by total volume of the composition, of a solvent composition comprising a zero VOC solvent selected from t-butylacetate, 1-bromopropane, benzotrifluoride, and a VOC solvent, and
5% to 75% of a polymeric or hydrocarbon resin.

9. The coating or ink resin-solvent composition of claim 8 wherein the zero VOC solvent is t-butylacetate.

10. The coating or ink resin solvent composition of claim 8 wherein the zero VOC solvent is 1-bromopropane.

11. The coating or ink resin solvent composition of claim 8 wherein the zero VOC solvent is benzotrifluoride.

12. An environmentally safe composition comprising a zero VOC blowing agent useful for the production of polyurethane foam, the composition comprising, by total weight of the composition:

1 to 100 parts by weight of a polyol;

1 to 50 parts by weight of toluene diisocyanate or methylene diphenylene diisocyanate;

2 parts by weight of water;
0.15 to 0.80 parts catalyst;
0.5 to 2 parts surfactant; and
4 to 20 parts acetone or methyl acetate.

10

13. An environmentally safe composition comprising a zero VOC blowing agent useful for the production of polyurethane foam, the composition comprising, by total weight of the composition:

15

1 to 100 parts by weight of a polyol;
1 to 50 parts by weight of toluene diisocyanate or methylene diphenylene diisocyanate;

20

2 parts by weight of water;
0.15 to 0.80 parts catalyst;
0.5 to 2 parts surfactant; and
4 to 20 parts 1-bromopropane.

14. An environmentally safe composition comprising a zero VOC blowing agent useful for the production of polyurethane foam, the composition comprising, by total weight of the composition:

5

1 to 100 parts by weight of a polyol;
1 to 50 parts by weight of toluene diisocyanate or methylene diphenylene diisocyanate;

10

2 parts by weight of water;
0.15 to 0.80 parts catalyst;
0.5 to 2 parts surfactant; and
4 to 20 parts 1-bromopropane blended with a zero VOC fluorinated compound.

15

15. An environmentally friendly adhesive, coating or ink solvent-resin composition comprising a solvent composition, said solvent composition comprising a high reactivity solvent (MIR greater than 1) and a low reactivity solvent (MIR less than 1), said low reactivity solvent being present in an amount effective to reduce the total reactivity of the solvent blend, said solvent composition being present in

an amount of from about 10% to about 90% by volume of the solvent-resin, further wherein the solvent resin composition comprises a polymeric or hydrocarbon resin, thereby producing an environmentally friendly adhesive, coating or ink composition.

16. The composition according to claim 15 consisting essentially of from about 10% to about 90% by volume of a low reactivity solvent (MIR less than 1) and about 5% to 45% of a polymeric or hydrocarbon resin.

17. An adhesive resin-solvent composition comprising:

40% to 90%, by total volume of the composition, of one or more zero

VOC solvents selected from the group consisting of:

1-bromopropane;

benzotrifluoride;

t-butylacetate;

methyl acetate;

acetone;

1,1,1,2,2,3,3,4,4-nonafluoro-4-methoxybutane;

1-ethoxy-1,1,2,2,3,3,4,4,4-nonafluorobutane;

2-(ethoxydifluoromethyl)-1,1,1,2,3,3,3-heptafluoropropane;

technical white oils (mineral oils) ; and

n-alkane (C12-C18);

5% to 35% of a hydrocarbon resin as a tackifier, and

5% to 40% of a resin, said resin comprising at least one resin

selected from the group consisting of styrene-butadiene, polychloroprene, polyvinyl chloride, acrylic, epoxy, urethane, nitrocellulose, and styrene polymer.

18. A coating or ink resin-solvent composition comprising:

10% to 90%, by total volume of the composition, of one or more zero

VOC solvents selected from the group consisting of:

1-bromopropane;

benzotrifluoride;

t-butylacetate;

methyl acetate;

10 acetone;
1,1,1,2,2,3,3,4,4-nonafluoro-4-methoxybutane;
1-ethoxy-1,1,2,2,3,3,4,4,4-nonafluorobutane;
2-(ethoxydifluoromethyl)-1,1,1,2,3,3,3-heptafluoropropane;
technical white oils (mineral oils); and
n-alkane (C12-C18);
a VOC solvent; and
15 5% to 75% of a polymeric or hydrocarbon resin.

19. A method for reducing the atmospheric reactivity of a solvent-resin composition, wherein the solvent-resin composition comprises from about 5% to about 95%, by total volume of the composition, of a solvent component, said solvent component comprising a reactive VOC solvent selected from the group consisting of:

xylene;
toluene;
n-methyl pyrrolidone;
hexane;
10 oxygenated solvents;
propylene carbonate;
glycol ethers;
trichloroethylene;
naphthenic solvents;
15 iso-paraffins;
epoxides;
acetals;
nitroparaffins;
terpene;
20 dimethyl ether;
esters;
ketones;
ethyl acetate;
alcohols;

25 paraffins;
 mineral spirits;
 dibasic esters;
 cycloalkanes; and
 cycloalkene,

30 wherein said solvent-resin composition has its atmospheric activity reduced by substituting from about 0.1% to about 99.9% of the reactive VOC solvent with a zero VOC solvent selected from the group consisting of:

- 35 1) 1-bromopropane;
 2) benzotrifluoride;
 3) t-butylacetate;
 4) methyl acetate;
 5) parachlorobenzotrifluoride;
 6) acetone;
 7) 1,1,1,2,2,3,3,4,4-nonafluoro-4-methoxybutane;
40 8) 1-ethoxy-1,1,2,2,3,3,4,4,4-nonafluorobutane;
 9) 2-(ethoxydifluoromethyl)-1,1,1,2,3,3,3-heptafluoropropane;
 10) technical white oils (mineral oils); and
 11) n-alkane (C12-C18).

20. The method of claim 19 wherein the resin is selected from the group consisting of adhesive resins, coating resins, ink resins, and blowing agent resins.

21. The method according to claim 19 wherein the solvent component is present in the amount of from about 10% to about 95% by total volume of the composition.

22. The method according to claim 19 wherein the solvent component is present in the amount of from about 30% to about 80% by total volume of the composition.

Abstract

This invention pertains to the art of solvent blends and solvent/resin blends. More particularly, this invention pertains to blends that reduce the atmospheric reactivity of some high volatile organic compounds. The invention is particularly applicable to solvent blends and solvent/resin blends that combine volatile organic compounds with newly discovered zero volatile organic compounds for use adhesives, coatings, inks, cleaning and blowing agents and the like and will be described with particular reference thereto. However, it will be appreciated that the invention may be advantageously employed in other environments and applications.

5

Attorney Docket No.: ACD 2 016-1-3

DECLARATION FOR PATENT APPLICATION

As a below named inventor, I hereby declare that:

My residence, post office address, and citizenship are as stated below next to my name.

I believe I am an original, first, and sole inventor of the subject matter which is claimed and for which a patent is sought on the invention entitled:

ZERO VOLITILE ORGANIC SOLVENT COMPOSITIONS

the specification of which is being filed with the U.S. Patent and Trademark Office herewith.

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37 Code of Federal Regulations § 1.56(a).

I hereby claim foreign priority benefits under Title 35, United States Code § 119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Not Applicable.

- 2 -

I hereby claim the benefit under Title 35, United States Code, § 119(e) of any United States provisional application(s) listed below:

Not Applicable.

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code § 112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, § 1.56(a) which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

U.S. Application Serial No. 09/022,779

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith.

Steven M. Auvil	Reg. No. 40,492	Mark E. Bandy	Reg. No. 35,788	Brian G. Bembenick	Reg. No. 41,463
John P. Cornely	Reg. No. 41,687	Joseph D. Dreher	Reg. No. 37,123	Christopher B. Fagan	Reg. No. 22,987
Jude A. Fry	Reg. No. 38,340	Steven M. Haas	Reg. No. 37,841	W. Scott Harders	Reg. No. 42,629
Michael E. Hudzinski	Reg. No. 34,185	Richard M. Klein	Reg. No. 33,000	Thomas E. Kocovsky, Jr.	Reg. No. 28,383
Sandra M. Koenig	Reg. No. 33,722	Brian E. Kondas	Reg. No. 40,685	Scott A. McCollister	Reg. No. 33,961
James W. McKee	Reg. No. 26,482	Richard J. Minnich	Reg. No. 24,175	Jay F. Moldovanyi	Reg. No. 29,678
Philip J. Moy	Reg. No. 31,280	Timothy E. Nauman	Reg. No. 32,283	Sue Ellen Phillips	Reg. No. 32,046
Patrick R. Roche	Reg. No. 29,580	Albert P. Sharpe, III	Reg. No. 19,879	R. Scott Speroff	Reg. No. 37,450
Mark S. Svat	Reg. No. 34,261				

- 3 -

Direct all telephone calls to: Timothy E. Nauman, Esq. at telephone number:

(216) 861-5582.

Address all correspondence to:

Timothy E. Nauman, Esq.
FAY, SHARPE, FAGAN, MINNICH & McKEE
1100 Superior Avenue - Suite 700
Cleveland, Ohio 44114-2518

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of sole inventor: RICHARD G. HENRY

Inventor's signature Richard G. Henry

Date: 02/25/00
Residence: Beachwood, OH 44122

Citizenship: U.S.A.

Post Office Address: 17 Bordeaux Lane
Beachwood, OH 44122

C:\DATA\2000\FEB\BGBVACD20161.3DE